



## TEST REPORT

TESTS	TEST METHODS*	RESULTS*
Apparent density	EN 14617-1:2005	2350 kg/m <sup>3</sup>
Water absorption	EN 14617-1:2005	0.04 %
Scratch resistance (polish)	EN 14617-4:2005	20.3 mm
Bending resistance	EN 14617-2:2008	43.4 MPa
Freezing and defrosting resistance	EN 14617-5:2005	Bending resistance after freezing and defrosting: 43.9 Mpa. Loss of bending resistance: -1.2 %
Chemical resistance	EN 14617-10:2005	Classification: C4
Tenacity	EN 14617-9:2005	5.50 J
Mohs Scale (hardness)	Referring to EN 101:1991	5.5
Slip resistance (polish)	EN 14231:2003	"dry" SRV: 48 "wet" SRV: 5
Thermal dilation	EN 14617-11:2005	24.3x10 <sup>-6</sup> /°C
Compression resistance	Referring to EN 14617-15:2005	210 MPa

\*Tests performed in Dec. 2012.